



## OMG 80 - PRODUCT SPECIFICATION

Non-covered spheroid atomized aluminum powder used in aluminothermia, epoxy resins, exothermal products, siderurgy, metallurgy and alike.

Chemical Composition	Unit	Essay	Average	
			Minimum	Maximum
ALUMINUM(Al)	%	ASTM E 1024-84	98,50	
IRON(Fe)	%	ASTM E 1024-84		1,00
SILICIUM(Si)	%	ASTM E 34-88		0,50
COPPER(Cu)	%	ASTM E 1024-84		0,25
ZINC(Zn)	%	ASTM E 1024-84		0,20
MAGNESIUM(Mg)	%	ASTM E 1024-84		0,60
MANGANESE(Mn)	%	ASTM E 1024-84		0,60
NICKEL(Ni)	%	ASTM E 1024-84		0,10
LEAD(Pb)	%	ASTM E 1024-84		0,05

### GRANULOMETRY (STANDARD)

		Unit	Essay	Minimum	Maximum
Mesh	Max. 100% 30 mesh passant	%	ASTM B 214-92		
Mesh	Min. 90% retained 325 mesh	%	ASTM B 214-92		
Mesh		%	ASTM B 214-92		
Mesh		%	ASTM B 214-92		
Mesh		%	ASTM B 214-92		

### APPARENT DENSITY

Unit	Essay	Minimum	Maximum
(g/cm <sup>3</sup> )	ASTM B 329-90	0,8	1,2

### STANDARD PACKAGING

<b>EOM 25:</b> 25 kg bags.
<b>EOM 1000:</b> Big Bag from 1,000 kg to 1,500 kg.

**ISO Certification 9001:2008**

ATOMIZAÇÃO DE METAIS ÔMEGA LTDA.  
 MATRIZ: Rua do Alumínio, 153 - CEP 08586-220 - Itaquaquetuba/SP  
 FILIAL: Rua do Bronze, 250 - CEP 08586-080 - Itaquaquetuba/SP  
 Central de Vendas: 55 11 4649-5555 / 4646-2566 / 7860-4404 (Nextel)  
 omega@omegametalurgia.com.br - www.omegametalurgia.com.br